

L-201

Epoxy Fiberply Prepreg



851 W. 18th Street
Costa Mesa, CA 92627
(949) 650-8106 Fax: (949) 631-6190
www.jdlincoln.com

Revised: 3/17/09

Product Data Sheet

Description

Fiberply L-201 is a unidirectional cross-plyed fiberglass prepreg face sheet with a flame retardant epoxy matrix. The fiberglass can be E-glass and/or S-2 ® glass. The impregnating resin is solution coated and cures in a broad temperature range.

Advantages of L-201

- ❖ Superior mechanical properties when compared to composites of woven prepreg because the fiberply process eliminates breaking, twisting, and intertwining of fibers caused by the weaving process.
- ❖ Improved strength and stiffness to weight ratios because excess resin deposits inherent with woven fiberglass prepreps are eliminated.
- ❖ Pre-plyed materials reduce the assembly labor in the production of sandwich panels.
- ❖ Reduced cost relative to woven prepreps because the complicated steps of weaving, stitching, heat - cleaning, and refinishing have been eliminated. The fiberply process produces adhesive prepreg directly from fiber and resin.

Physical Properties

- *Standard Weight:* 0.175 lbs/ft² (855 g/m²)
- *Standard Resin Content:* 45% by weight
- *Volatile Content:* 2% maximum
- *Standard Tack:* Press Grade Medium
- *Specific Gravity:* 1.75
- *Other Weights, Resin Contents, and Fibers are Available*

Availability

- 50" x 122" Sheets (127 cm x 310 cm)
- 50" x 147" Sheets (127 cm x 373 cm)



851 W. 18th Street
Costa Mesa, CA 92627
(949) 650-8106 Fax: (949) 631-6190
www.jdlincoln.com

L-201

Shelf Life

- *6 months at 0°F (-18°C)*
- *14 days at Room Temperature (70°F or 21°C)*

Cure Cycle

- *90 minutes at 270°F (132°C)*

Adhesive / Scrim Options

The customer may request an adhesive film be applied to one or both sides or a fiberglass scrim to one or both sides to improve bonding and/or handling characteristics.

NOTICE:

Product data and parameters cited in this publication have been obtained in J.D. Lincoln, Inc. laboratories using the materials under carefully controlled conditions. The information, therefore, is believed to be accurate and correctly stated. Data of this type may be considered to be indicative of representative properties obtainable. J.D. Lincoln, Inc. cannot accept responsibility for the misapplication of these products, nor for their use under uncontrolled conditions. Numerical values resulting from the application of this material are dependant on processing details. It is recommended that the user develop his or her own application techniques and generate data consistent with his or her specific application and process.