

# L-306-2

## Core Edge Filler, One-component



851 W. 18<sup>th</sup> Street  
Costa Mesa, CA 92627  
(949) 650-8106 Fax:(949) 631-6190  
[www.jdlincoln.com](http://www.jdlincoln.com)

## Product Data Sheet

Revised: 3/18/09

### Description

L-306-2 is a lightweight, thermosetting paste adhesive core filler. L-306-2 is easily applied with trowl or spatula into honeycomb core for creating structural hard points or subsequent mechanical attachments. L-306-2 is a low sag, 250°F (121°C) curing system yielding high local compressive strength with excellent adhesion to both sandwich facing and core.

### Advantages of L-306-2

- ❖ L-306-2 exhibits extremely high local compressive strengths.
- ❖ L-306-2 co-cures with various resin systems to allow the user to create attachment points in sandwich panels without secondary potting.

### Physical Properties

- *One Component*
- *Color: Cream*
- *Density: 90 lbs/ft<sup>3</sup> (1.44 g/mL)*
- *Form: Heavy Paste*

### Availability

- *5 Gallon Containers (18.9 L)*

### Shelf Life

- *6 months at 40°F (4°C)*
- *4 days at Room Temperature (454 gram mass)*
- *Caution – avoid masses of over 1 pound (454 grams) at Room Temperature.*



851 W. 18<sup>th</sup> Street  
Costa Mesa, CA 92627  
(949) 650-8106 Fax: (949) 631-6190  
[www.jdlincoln.com](http://www.jdlincoln.com)

L-306-2

## Cure Cycle

- 1 Hour at 250-260°F (121°C–127°C)

## Average Mechanical Properties

### Compressive Strength (ASTM D 695)

- RT (75°F or 23°C) 19,500 PSI (134 MPa)

### Overlap Tensile Strength (ASTM D1002)

- RT (75°F or 23°C) 2800 PSI (19.3 MPa)
- 160°F (71°C) 2900 PSI (20.0 MPa)

CAUTION: Care should be taken with batches over one pound total weight. Large batches or those which are applied in excess of this amount may become exothermic during cure (i.e., VERY HOT). The user is encouraged to develop standard application quantities.

#### NOTICE:

Product data and parameters cited in this publication have been obtained in J.D. Lincoln, Inc. laboratories using the materials under carefully controlled conditions. The information, therefore, is believed to be accurate and correctly stated. Data of this type may be considered to be indicative of representative properties obtainable. J.D. Lincoln, Inc. cannot accept responsibility for the misapplication of these products, nor for their use under uncontrolled conditions. Numerical values resulting from the application of this material are dependant on processing details. It is recommended that the user develop his or her own application techniques and generate data consistent with his or her specific application and process.