

L-314

Modified Epoxy Film Adhesive, High Toughness



851 W. 18th Street
Costa Mesa, CA 92627
(949) 650-8106 Fax:(949) 631-6190
www.jdlincoln.com

Product Data Sheet

Revised: 4/29/09

Description

L-314 is a toughened, modified epoxy adhesive film with heat resistance suitable for a wide variety of applications. Metallic or non-metallic substrates may be bonded with L-314 to provide a tough, durable, structural joint with excellent resistance to temperatures up to 250°F (121°C). Facings may be bonded to aluminum or aramid / phenolic honeycomb core. L-314 may be cured over a broad range of time, temperature, and pressure cycles to match the requirements of the manufacturer's process or curing equipment.

Advantages of L-314

- ❖ Film weights as low as 0.005 lbs/ft² (24 g/m²) can be manufactured for ultra lightweight designs such as aerospace components or electronics components.
- ❖ L-314 will co-cure well with many of today's modern epoxy matrix composites.
- ❖ L-314 may be reticulated by the user to minimize the total weight of a sandwich structure.
- ❖ Room temperature outlife exceeds 7 days at 75°F (24°C) or below.

Physical Properties

- *Standard Weight:* 0.030 lbs/ft² (146 g/m²)
- *Optional Weights:* 0.005 lbs/ft², 0.0045 lbs/ft², 0.060 lbs/ft² (other weights are available)
- *Standard Thickness:* 0.011" (0.279 mm) Nominal
- *Volatile Content:* Less than 2.0%
- *Tack:* Light Tack

Availability

- 36" Wide Rolls x 80 Yards Long (91 cm x 73 m)
- 50" Wide Rolls x 80 Yards Long (127 cm x 70 m)
- 60" Wide Rolls x 80 Yards Long (152 cm x 70 m)



851 W. 18th Street
Costa Mesa, CA 92627
(949) 650-8106 Fax: (949) 631-6190
www.jdlincoln.com

L-314

Shelf Life

- 6 months at 0°F (-18°C)
- 7 days at Room Temperature (75°F or 24°C)

Cure Cycles

- 120 minutes at 225°F (107°C), or
- 60 minutes at 250°F (121°C), or
- 40 minutes at 275°F (135°C).

Adhesive Primers

L-314 is designed to be used with:

- *L-319-1 Corrosion Inhibiting Adhesive Primer*

Applicable Documents

- *MMM-A-132*
- *MIL-A-25463*

Mechanical Properties: 0.060 lbs/ft² (292 g/m²) Adhesive Film

Property	25 PSI (0.17 MPa) Cure in Platen Press	Press Cure after 1 Month Outlife	Test Method
Tensile Shear Strength			
-67°F (-55°C)	6,700 PSI (46.2 MPa)	6,680 PSI (46.0 MPa)	ASTM D1002
Room Temp	5,900 PSI (40.6 MPa)	5,950 PSI (41.0 MPa)	ASTM D1002
180°F (82°C)	4,600 PSI (31.6 MPa)	4,500 PSI (31.0 MPa)	ASTM D1002
250°F (121°C)	2,250 PSI (15.5 MPa)	2,000 PSI (13.8 MPa)	ASTM D1002
Sandwich Peel Strength			
-67°F (-55°C)	42 in lb/in (187 Nm/m)	40 in lb/in (178 Nm/m)	ASTM D1781
Room Temp	39 in lb/in (173 Nm/m)	35 in lb/in (156 Nm/m)	ASTM D1781
180°F (82°C)	35 in lb/in (156 Nm/m)	32 in lb/in (142 Nm/m)	ASTM D1781
Flatwise Tensile Strength			
-67°F (-55°C)	1,250 PSI (8.6 MPa)	1,140 PSI (7.9 MPa)	ASTM C297
Room Temp	1,120 PSI (7.7 MPa)	1,100 PSI (7.6 MPa)	ASTM C297
180°F (82°C)	660 PSI (4.5 MPa)	620 PSI (4.3 MPa)	ASTM C297
Sandwich Flexural Strength			
-67°F (-55°C)	core failure	core failure	ASTM C393
Room Temp	core failure	core failure	ASTM C393
180°F (82°C)	core failure	core failure	ASTM C393
T-Peel Strength			
-67°F (-55°C)	52 lb/in (231 N/25 mm)	50 lb/in (223 N/25 mm)	ASTM D1876
Room Temp	49 lb/in (218 N/25 mm)	47 lb/in (209 N/25 mm)	ASTM D1876
180°F (82°C)	41 lb/in (182 N/25 mm)	40 lb/in (178 N/25 mm)	ASTM D1876
Floating Roller Peel Strength			
-67°F (-55°C)	105 lb/in (467 N/25mm)	104 lb/in (463 N/25 mm)	ASTM D3167
Room Temp	95 lb/in (423 N/25 mm)	94 lb/in (418 N/25 mm)	ASTM D3167
180°F (82°C)	85 lb/in (378 N/25 mm)	82 lb/in (365 N/25 mm)	ASTM D3167

NOTICE:

Product data and parameters cited in this publication have been obtained in J.D. Lincoln, Inc. laboratories using the materials under carefully controlled conditions. The information, therefore, is believed to be accurate and correctly stated. Data of this type may be considered to be indicative of representative properties obtainable. J.D. Lincoln, Inc. cannot accept responsibility for the misapplication of these products, nor for their use under uncontrolled conditions. Numerical values resulting from the application of this material are dependant on processing details. It is recommended that the user develop his or her own application techniques and generate data consistent with his or her specific application and process.