

# L-929(GT300)

## Solution Coated UD Epoxy Prepreg



851 W. 18<sup>th</sup> Street  
Costa Mesa, CA 92627  
(949) 650-8106 Fax:(949) 631-6190  
[www.jdlincoln.com](http://www.jdlincoln.com)

### Product Data Sheet

Revised: 2/8/10

#### Description

L-929(GT300) is a solution coated unidirectional epoxy prepreg with excellent mechanical properties. It is a versatile “general purpose” prepreg which can be cured over a broad range of temperatures and pressures. L-929(GT300) is also available in woven fabric up to 60” (152 cm) wide. Typical designations for woven material would be L-929-100-50”.

#### Advantages of L-929(GT300)

- ❖ Thorough wetting of carbon fiber yields a product exhibiting outstanding flexural and compressive strength.
- ❖ L-929(GT300) may be used in applications with a service temperature up to 180°F (82°C).
- ❖ L-929(GT300) performs well in sporting goods, automotive and other commercial applications.

#### Physical Properties on GT300 Carbon Fiber

- *Fiber Areal Weight:* 0.030 lbs/ft<sup>2</sup> (145 g/m<sup>2</sup>)
- *Standard Resin Content:* 35% by weight
- *Volatile Content:* 2% max
- *Standard Tack:* Medium
- *Cured Ply Thickness:* 0.0055” (0.140 mm)
- *Other Weights, Resin Contents, and Fabrics are Available.*

#### Availability

- *Up to 24” width in rolls up to 100 yards long (61 cm x 91 m)*
- *Slitting to narrow widths available*

#### Shelf Life

- *6 months at 40°F (4°C) or below*
- *14 days at room temperature (70°F or 21°C)*



851 W. 18<sup>th</sup> Street  
Costa Mesa, CA 92627  
(949) 650-8106 Fax: (949) 631-6190  
[www.jdlincoln.com](http://www.jdlincoln.com)

L-929(GT300)

## Cure Cycles

- 60 minutes at 250-275°F (121-135°C) with 50 PSI (0.35 MPa) minimum.
- Vacuum bag / oven cures are acceptable for many applications.

## Typical Applications

- Business Aircraft Panel Facings
- Auto racing components
- Motorcycle components
- Sporting goods
- Panel Stiffeners for marine

(GT300 Fiber = Generic 32 MM Modulus Fiber)

## Mechanical Data

PROPERTY	LAMINATE PROPERTIES	
	100 PSI (0.69 MPa) CURE	TEST METHOD
<b>ULTIMATE TENSILE (0°) STRENGTH</b> Room Temperature (RT) 160°F (71°C)	220 KSI (1517 MPa) 200 KSI (1379 MPa)	ASTM D638 ASTM D638
<b>TENSILE (0°) MODULUS</b> Room Temperature (RT) 160°F (71°C)	18.0 MSI (124 GPa) 17.5 MSI (121 GPa)	ASTM D638 ASTM D638
<b>ULTIMATE FLEXURAL (0°) STRENGTH</b> Room Temperature (RT) 160°F (71°C)	220 KSI (15117 MPa) 185 KSI (1276 GPa)	ASTM D790 ASTM D790
<b>FLEXURAL (0°) MODULUS</b> Room Temperature (RT) 160°F (71°C)	17.0 MSI (117 GPa) 16.5 MSI (114 GPa)	ASTM D790 ASTM D790
<b>SHORT BEAM SHEAR (0°) STRENGTH</b> Room Temperature (RT)	15 KSI (103 MPa)	ASTM D2344

### NOTICE:

Product data and parameters cited in this publication have been obtained in J.D. Lincoln, Inc. laboratories using the materials under carefully controlled conditions. The information, therefore, is believed to be accurate and correctly stated. Data of this type may be considered to be indicative of representative properties obtainable. J.D. Lincoln, Inc. cannot accept responsibility for the misapplication of these products, nor for their use under uncontrolled conditions. Numerical values resulting from the application of this material are dependant on processing details. It is recommended that the user develop his or her own application techniques and generate data consistent with his or her specific application and process.